

# Checklist for LJS/VRAM Application

## Pre-Application

- The existing surface of the application area shall be clean and free of dirt, dust and any debris and free of moisture. Do not apply over temporary traffic control tape; ensure that it is removed prior to placement.
- Ensure that any depressions, potholes, wide cracks, etc. have been addressed with prep work through patching or sealing.

## Application

- It is highly recommended the applicator check his application rate in a staging area prior to performing on the project.
- Apply LJS/VRAM between 265F and 320F. If needed, reheat gradually with agitation to prevent localized overheating.
- Exact location of LJS/VRAM should be discussed prior to performing on the project.
- Check the application rate within the first 1,000 feet of placement, then every 12,000 feet thereafter.
- Ensure the application width is within the acceptable parameters and the initial placement of the material does not flow more than 2" from that initial application.
- Check for pickup or tracking of material by driving across the material within 30 minutes of initial application.
- Public and construction vehicles may cross over the LJS/VRAM band once it has cooled to 130F or less. **Do not permit** public and construction vehicles to stop upon or drive longitudinally directly on top of the LJS/VRAM band.
- It is usually needed for the area of application to be painted with marking paint as a guideline for the applicator to follow.
- When sampling, use the sampling spigot. **Do not obtain the sample from the spray bar to minimize contamination.**
- It is suggested that sampling be done at the time of the first required field rate check. It is **recommended** that the applicator **should** retain a sister sample of the material at the same time an agency sample is provided.

## Paving

- Align the HMA paver screed edge end plate (aka: door, wing, end gate, slide plate) so as to split the finished application of LJS/VRAM so as the new longitudinal joint will meet ½ way across the finished application of material.
- Ensure the paver end plate (aka: door, wing, end gate, slide plate) is raised slightly above the finished LJS/VRAM so as not to drag on or through the material.
- If using grade skis during the HMA installment; ensure they do not run on top of the finished LJS/VRAM application.
- In hot weather and when trucks pull away from the paver and cross the LJS/ VRAM, it may be susceptible to peeling due to tack coat on the tires. A light mist of water on the surface of the LJS/VRAM is usually an adequate bond breaker to prevent this.
- Use the rolling pattern determined for the project.
- Do not use pneumatic rollers on HMA directly over the LJS/VRAM.
- When rolling the HMA over the LJS/VRAM, allow for the edge of the drum to overhang a few inches beyond the edge of the HMA mat. Avoid placing the edge of the drum directly over the HMA on the inside edge of the LJS/VRAM.
- Newly compacted HMA directly above the LJS/VRAM placement may feel spongy to walk on for several minutes. This indicates that the LJS/VRAM is hot and migrating into the mix. This area will stiffen when cool.
- Density requirements are waived on the HMA within one foot on either side of the joint placed over the LJS/VRAM.
- If conditions warrant to leave VRAM/LJS open to traffic or a hot surface temperature is expected, primarily on a milled surface, an application of natural or crushed sand, or lime, may be applied at a rate of 1 +/- ½ lb/SY with a spreading device (i.e.: push drop spreader), or by hand. Sanding should also be considered if rain is likely.

## Rumble strips / raised pavement markers (RPMs)

- When installing Rumble Strips and/or RPM's and surface temperature is over 120°F prior to cutting, it is highly recommended watering designated area with a water truck or a pump assisted device to cool down work area. Clean debris out of Rumble Strips as soon as possible with a power broom directly behind the milling machine before millings can bind together.

**Warning:** In the event of a rain or snow fall the surface of uncovered installed product may be slippery when wet.

Should you have any questions please feel free to contact any of our representatives listed below.

Jim Cunningham	412.817.8482	Tim Zahn	217.494.3563
Andrew Eicher	317.371.0527	Chad Crosby	419.769.0793
Dave Stanczak	847.638.0076	Jeff Tidaback	224.254.3347
Todd Thomas	973.610.2260	Vince Venturella	317.403.1978

